




## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification <sup>6</sup> : <b>G05G 1/00, 3/00</b>	<b>A1</b>	(11) International Publication Number: <b>WO 97/09664</b> (43) International Publication Date: <b>13 March 1997 (13.03.97)</b>
(21) International Application Number: <b>PCT/US96/13927</b> (22) International Filing Date: <b>30 August 1996 (30.08.96)</b> (30) Priority Data: <b>08/523,262</b> <b>5 September 1995 (05.09.95)</b> <b>US</b> (71) Applicant: <b>UNIVERSITY OF CHICAGO [US/US]; 1101 East 58th Street, Chicago, IL 60637 (US).</b> (72) Inventors: <b>HULL, John, R.; 5519 South Bruner, Hinsdale, IL 60521 (US). MULCAHY, Thomas, M.; 4031 Clausen Avenue, Western Springs, IL 60558 (US).</b> (74) Agents: <b>RECHTIN, Michael, D. et al.; Reinhart, Boerner, Van Deuren, Norris &amp; Rieselbach, S.C., Suite 2100, 1000 North Water Street, P.O. Box 92900, Milwaukee, WI 53202-0900 (US).</b>	(81) Designated States: <b>AL, AM, AT, AU, AZ, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IL, IS, JP, KE, KG, KP, KR, KZ, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, UZ, VN, ARIPO patent (KE, LS, MW, SD, SZ, UG), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).</b>  <b>Published</b> <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>	

(54) Title: IMPROVEMENTS IN MIXED-MU SUPERCONDUCTING BEARINGS

## (57) Abstract

A mixed-mu superconducting bearing (10) including a ferrite structure (20) disposed for rotation adjacent a stationary superconductor material structure (14) and a stationary permanent magnet structure (12). The ferrite structure (20) is levitated by said stationary permanent magnet structure (12).



BEST AVAILABLE COPY

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgyzstan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	KZ	Kazakhstan	SG	Singapore
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovakia
CM	Cameroon	LR	Liberia	SN	Senegal
CN	China	LT	Lithuania	SZ	Swaziland
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	LV	Latvia	TG	Togo
DE	Germany	MC	Monaco	TJ	Tajikistan
DK	Denmark	MD	Republic of Moldova	TT	Trinidad and Tobago
EE	Estonia	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	UG	Uganda
FI	Finland	MN	Mongolia	US	United States of America
FR	France	MR	Mauritania	UZ	Uzbekistan
GA	Gabon			VN	Viet Nam

## IMPROVEMENTS IN MIXED-MU SUPERCONDUCTING BEARINGS

Background of the Invention

This patent application is a continuation-in-part patent application of United States Patent Application Serial No. 08/025,950, filed March 3, 1993. The United States government has rights in this invention pursuant to Contract W-31-109-ENG-38 between the United States Department of Energy and the University of Chicago, representing Argonne National Laboratory.

The present invention is directed to superconducting bearings. More particularly, the present invention is directed to superconducting bearings offering increased stability and levitation force, as well as the structural integrity to rotate at very high speeds.

When superconducting bearings are used in flywheel energy storage devices, the efficiency of the flywheel can be very high and flywheels of this type become economic for diurnal energy storage and other applications where high energy efficiency is important. Diurnal storage of electricity is important to electric utilities in order to efficiently utilize base load generating plants and to meet the varying load demands of their customers. For example, the base load generating plants can charge storage units at night when demand is low. Peak electrical demands can then be met by discharging the storage units during the daytime peak hours. Energy storage can also play a substantial role in eliminating or postponing the installation of power lines with larger capacity. Power can be transmitted at night to a substation or user energy storage unit when demand is low, and then during peak power times, the energy storage units can be discharged. The placement of the energy storage units can occur in various parts of the electrical distribution system: utility parks where large amounts of energy are stored; in tandem with photovoltaic or wind energy generation facilities that are time dependent; substation units; individual companies and houses. The invention can also be used for energy storage on electric vehicles such as cars and buses, or as wayside energy storage for electric trains or other transit vehicles.

Flywheels are often considered for energy storage applications. Their primary advantages are modularity, mechanical simplicity (low cost), high energy storage density

(Wh/kg), and high efficiency input and output of electrical energy. The ability to produce high strength flywheel rotors and the ability to efficiently transfer energy in and out of a flywheel are well known and will not be discussed herein.

The primary disadvantage of conventional flywheels is inefficiency in standby storage mode. These losses occur because the bearings that support the flywheel structure produce high rotational losses. The present invention provides bearings having very low rotational losses and can enable standby losses in flywheels to be 0.1%/hr or less. High temperature superconductor bearings designed in accordance with one form of the invention provide passive stability in all directions; i.e., they provide a positive stiffness in all displacement directions. Further, they allow rotational motion with very low friction.

A preferred high temperature superconductor bearing embodiment of the present invention provides a number of improvements that decrease rotational losses and overcome reluctance instability. Other forms of the invention provide these advantages and incorporate a ferromagnetic part of a rotor directly into the composite winding of the flywheel, allowing even higher rotor speeds to be obtained. Another preferred embodiment enables greater levitation force to be produced while still providing other previously described advantages of the invention.

It is therefore an object of the present invention to provide a low-loss mixed- $\mu$  high temperature superconductor bearing that can enable a flywheel energy storage device to be highly efficient.

It is a further object of the present invention to provide novel method and apparatus that overcome reluctance instabilities in mixed- $\mu$  high temperature superconductor bearings.

It is a further object of the present invention to provide a mixed- $\mu$  high temperature superconductor bearing capable of rotating at high velocities without sacrificing the bearing's structural integrity.

It is a further object of the present invention to provide high levitation pressures in a mixed- $\mu$  high temperature superconductor bearing.

These objects and other advantages of the invention will be readily apparent from the following description of the preferred embodiments thereof, taken in conjunction with the accompanying drawings described hereinbelow.

#### Brief Description of the Drawings

FIG. 1 illustrates a mixed-mu bearing constructed in accordance with one form of the invention;

FIG. 2A shows a mixed-mu bearing without reluctance instability effects, and FIG. 2B shows a mixed-mu bearing experiencing reluctance instability;

FIG. 3 illustrates the coefficient of friction of a mixed-mu bearing as a function of rotor rim velocity; and

FIG. 4 shows a top view of a mixed-mu bearing rotor using ferrite or steel wedges to increase radial and circumferential reluctance;

FIG. 5 illustrates a top view of a mixed-mu bearing rotor including ferrite or steel pins;

FIG. 6 shows a top view of a mixed-mu bearing including staggered ferrite or steel pins;

FIG. 7 illustrates a side view of an alternative embodiment of a mixed-mu bearing with a rotor surface shaped to lessen the effects of reluctance instability;

FIG. 8 shows another alternative embodiment of a mixed-mu bearing design capable of achieving large levitation force; and

FIG. 9 shows an alternative embodiment of the bearing shown in FIG. 8.

#### Detailed Description of Preferred Embodiments

A basic mixed-mu bearing constructed in accordance with one form of the invention is indicated generally at 10 in FIG. 1. The basic mixed-mu bearing 10 is preferably comprised of a stationary permanent magnet system, stationary high-temperature superconductors, and a rotating ferromagnet (e.g., magnetic steel). The bearing 10 is referred to as "mixed-mu" because of the use of both ferromagnetic ( $\mu > 1$ ) and diamagnetic ( $\mu < 1$ ) phenomena in the levitation, where "mu" refers to the magnetic permeability of a component.

A first stationary permanent magnet 12 is fixed above and adjacent a stationary upper high temperature superconductor 14 and a second permanent magnet 16 is disposed below and adjacent a stationary lower high temperature superconductor 18. A rotor 20 is disposed for rotation vertically between the two stationary permanent magnet/high temperature superconductor pairs as shown in FIG. 1. While the rotor 20 can comprise a variety of durable materials, preferably ferromagnetic material, such as steel, is used.

The entire bearing 10 is field-cooled (i.e., the high temperature superconductors 14 and 18 are immersed in liquid nitrogen until their temperature lowers sufficiently to enter the superconducting state) with the rotor 20 at approximately vertical equilibrium (with the upward magnetic force nearly balancing the downward gravitational force). The high temperature superconductors 14 and 18 are encased in a conventional liquid nitrogen cryogenic chamber, which is not shown for increased clarity. The entire bearing assembly is encased in a conventional vacuum chamber, which is also not shown.

The permanent magnets 12 and 16 are both polarized vertically in the same direction and induce magnetization in the rotor 20. Without the high temperature superconductors 14 and 18 in the superconducting state, the bearing 10 is radially stable but vertically unstable. Accordingly, the rotor 20 generally stays centered along its vertical axis of symmetry, but either falls toward the second permanent magnet 16 or rises toward the first permanent magnet 12. Because of the diamagnetic properties of the high temperature superconductors 14 and 18, magnetization of the steel in the rotor 20 induces shielding currents in the high temperature superconductors 14 and 18. This results in a repulsive force between the high temperature superconductors 14 and 18 and the steel in the rotor 20 in this embodiment. This repulsive force increases as the distance between the steel and one of the high temperature superconductors 14 and 18 decreases. This diamagnetic property tends to stabilize the bearing 10 in the vertical direction. When the steel is close enough to one of the high temperature superconductors 14 and 18, the stabilizing influence of one of the high temperature superconductors 14 and 18 is enough to overcome the destabilizing influence of the permanent magnet/rotor interaction.

Flux pinning in the high temperature superconductors 14 and 18 further acts to stabilize the bearing 10. This flux pinning is most evident with "Type II" superconductor materials that allow some magnetic flux to enter the materials. Once the high temperature superconductors 14 and 18 are field-cooled, one or more of the permanent magnets 12 and 16 can be moved vertically to adjust the vertical position of the rotor.

The present invention can also work with only a single high temperature superconductor or single permanent magnet as discussed in the parent application (United States Patent Application Serial No. 08/025,950, filed March 3, 1993) of the present application. Alternatively, additional superconductors and magnets can be added to the embodiments disclosed herein without departing from the invention.

In another preferred embodiment of the invention, rotational losses are lessened by using permanent magnets 12 and 16 with a high degree of rotational symmetry. To a first approximation, the high temperature superconductors 14 and 18 experience a constant magnetic field and no loss. The only actual losses are the hysteresis and eddy currents in the rotating rotor 20 (which preferably comprises steel) which are extremely small. High mechanical strength of the rotor 20 allows the rotor 20 to spin very fast without structural failure or degradation.

During experiments on the mixed-mu high temperature superconductor bearing 10, it was noted that some geometries exhibit a reluctance instability. The instability is especially prominent for geometries of the rotor 20 in which the radius is larger than the height of a cylindrical shell or tube-shaped rotor 20.

The basic configuration of the reluctance instability is illustrated by FIGS. 2A and 2B. The preferred levitational orientation of the rotor 20 is shown in FIG. 2A. The air gap in a magnetic circuit in the vicinity of the rotor 20 is composed of distances 22a plus 24a. FIG. 2B illustrates the position of the rotor 20 when the instability is active and the rotor 20 tilts. It is seen here that the effective air gap 22b plus 24b is diminished compared with FIG. 2A. Because the  $\mu$  of the rotor is so much larger than that of air, the magnetic flux prefers to go directly through smaller air gaps 22b and 24b and diagonally through the

rotor 20. In other words, the total reluctance decreases when the rotor 20 tilts. This is the basis of the reluctance instability.

It has been shown that long narrow cylinders or shells can be stably levitated, whereas squat cylinders or rings undergo substantial reluctance instability. However, for many practical applications, it is desirable to construct the rotors 20 with short height. Preferred embodiments of the invention can overcome the reluctance instability in the mixed- $\mu$  high temperature superconductor bearing 10.

As an indication of the low friction potential of the mixed- $\mu$  high temperature superconductor bearing 10, the coefficient of friction (hereinafter "COF") as a function of the rim velocity of the rotor 20 is shown in FIG. 3. In this case, the rotor 20 comprised a Mn-ferrite sintered material. The advantage of such a rotor 20 over a steel form of the rotor 20 is that the electrical conductivity of the ferrite is much smaller, so that eddy current losses are small. No special attempt was made to use uniform permanent magnets in this experiment, and the losses could be made even smaller if a more homogeneous set of the permanent magnets 12 and 16 were used. A linear extrapolation of the COF shows that a rim velocity greater of 100 m/s would be reached before the COF reached  $1.0 \times 10^{-6}$ . Such a low value (compared to prior art designs) verifies this structure can be useful for a low-loss flywheel energy storage system.

Another preferred embodiment of the present invention locates the rotor 20 such that the rotor 20 is adjacent an air gap in the radial or azimuthal direction. If the rotor 20 begins to tilt, the total reluctance of the magnetic system is increased. The ferrite rotor 20 that was used in the experiment (whose results are shown in FIG. 3) is preferably constructed in this manner. Preferably, a significant gap of nonmagnetic material is provided between each of the ferrite grains.

In all embodiments of the present invention where permanent magnets are not part of the rotor 20, the rotor 20 is preferably mechanically constrained before and during (but not after) the field cooling of the superconductors 14 and 18. It will be apparent that the rotor 20 can comprise any material with high magnetic permeability (e.g., ferrite, magnetic steels or nickel and its alloys) and is preferably of high mechanical strength. Further, the



rotor 20 can comprise a wide variety of shapes including, but not limited to, cylinders, rings and even non-circular shapes.

The rotor 20 can also comprise a variety of materials in various shapes and configurations. For example, electrically nonconductive magnetic ferrite can be sintered into the shape desired for the rotor 20. Alternatively, ferrite powder can be mixed or placed into an epoxy or other nonconducting, nonmagnetic matrix. Another preferred embodiment uses steel, nickel, or other conductive powder in a sintered form or in an epoxy or other nonmagnetic matrix. Yet another embodiment uses the ferrite powder as ballast in the winding of a fiber composite ring (or other desired shape). Composite rings can be formed by incorporating a powdered mass or "ballast" into the matrix material (usually epoxy). By changing the density of the composite as a function of radius, radial stresses in the final composite can be minimized or eliminated. Because the composite is mechanically weakest in the radial direction, this allows the composite to spin faster before breaking. By using ferrite (or steel) powder as the ballast, the mechanical strength of the bearing rotor 20 is maximized and there is a significant radial (and circumferential) reluctance to overcome any reluctance instability.

A further preferred embodiment of the invention embodiment is shown in a horizontal cross-sectional view in FIG. 4. The figure is shown for the rotor 20 having a ring geometry 30, but can also take the form of a cylinder or other similar shape. Alternate steel (or ferrite) wedges 32 are separated by nonmagnetic wedges 34 such as epoxy or composite-epoxy. The entire ring 30 can be optionally surrounded by a composite ring 36 to increase the overall mechanical integrity when the rotor 20 is spun to high speeds. The nonmagnetic wedges 34 provide the desired reluctance in the circumferential direction.

A further embodiment based around the geometry shown in FIG. 4 uses the steel wedges 32 constructed from nonisotropic laminations so that there is a higher magnetic permeability  $\mu$  value in the vertical direction than in the azimuthal direction. Another preferred embodiment of this type is shown in FIG. 5, in which a series of steel (or ferrite) pins 38 is located within a nonmagnetic matrix 40. The pins 38 can also be staggered in the azimuthal direction as shown in Fig 6.

A disadvantage of the geometries shown in Figs. 4-6 is that the magnetization of the rotor 20 is not homogeneous in the azimuthal direction. This inhomogeneity will induce hysteresis losses in the high temperature superconductor components as the rotor 20 rotates. To partially overcome this disadvantage, the top and bottom of the rings 30 can be covered by a ferromagnetic plate 42. The thickness of the ferromagnetic plate is preferably thin relative to the height of the steel wedges 32 or pins 38. The ferromagnetic plate 42 smooths out the inhomogeneities experienced by the high temperature superconductors 14 and 18.

Another preferred embodiment shapes the bottom of the rotor 20, as shown in FIG. 7, so that the reluctance increases if the rotor 20 is tipped. While this simplifies the construction of the rotor 20, it complicates the high temperature superconductors 14 and 18 and high temperature superconductor-cryostat construction. It is desirable to have the high temperature superconductors 14 and 18 as close to the rotor 20 as possible in order to maximize stability. The preferred embodiment of FIG. 7 can provide this advantageous result.

One of the disadvantages of the geometry shown in FIG. 1 is that the levitational force is not very large. If the magnetic field is large enough to saturate the magnetization of the rotor 20, it will have nearly constant magnetization  $M$ . Then the levitation force  $F$  per unit volume will be given by

$$F = M \, dH/dz,$$

where  $H$  is the applied magnetic field and  $z$  is the vertical coordinate. Ideally, one desires  $dH/dz$  to be uniform over the volume of the rotor 20. If  $dH/dz$  is not uniform, then the magnetic system produces a magnetic stiffness on the rotor 20. This stiffness is always destabilizing. To stabilize the rotor 20,  $dH/dz$  should be as large as possible, with  $d^2H/dz^2$  as small as possible.

An embodiment to achieve large levitation force in a mixed- $\mu$  high temperature superconductor bearing is shown in FIG. 8 for a ring geometry. The bearing assembly 50 comprises an upper permanent magnet 52, a lower permanent magnet 54, an upper high temperature superconductor 56, a lower high temperature superconductor 58, an iron flux

return path 60, and a ring-shaped ferromagnetic rotor 62. The dimensions of the permanent magnets 52 and 54 are chosen so as to minimize  $d^2H/dz^2$ . In a variation on this embodiment additional permanent magnets and iron pole pieces 64 can be inserted into the system to further minimize  $d^2H/dz^2$ , as shown for example in FIG. 9.

The preferred embodiments of the present invention provide a low-loss mixed-mu high temperature superconductor bearings that can be used to achieve a high-efficiency flywheel energy storage device. The configurations also overcome reluctance instabilities in mixed-mu high temperature superconductor bearings, are able to obtain high speeds, and high levitation pressures.

While preferred embodiments of the invention have been shown and described, it will be clear to those skilled in the art that various changes and modifications can be made without departing from the invention in its broader aspects as set forth in the claims provided hereinafter.

**What Is Claimed Is:**

1. A mixed-mu superconducting bearing, comprising:  
a ferrite structure disposed for rotation adjacent a stationary superconductor material structure and a stationary permanent magnet structure, said ferrite structure being levitated by said stationary permanent magnet structure.
2. The bearing as defined in claim 1, wherein said ferrite structure comprises sintered ferrite.
3. The bearing as defined in claim 1, wherein said ferrite structure includes a ferrite disposed in an epoxy matrix.
4. The bearing as defined in claim 1, wherein said ferrite structure includes ferrite powder mixed with a fiber composite winding.
5. A mixed-mu superconducting bearing, comprising:  
a steel structure disposed for rotation adjacent a stationary superconductor material structure and a stationary permanent magnet structure, said steel structure being levitated by said stationary permanent magnet structure.
6. The bearing as defined in claim 5, wherein said steel structure includes steel powder mixed with a fiber composite winding.
7. The bearing as defined in claim 5, wherein said steel structure includes steel powder in an epoxy matrix.
8. A mixed-mu superconducting bearing, comprising:  
a rotor disposed for rotation adjacent a stationary superconductor material structure and a stationary permanent magnet structure, said rotor comprising alternating ferromagnetic and nonferromagnetic structures.
9. The bearing as defined in claim 8, wherein said alternating ferromagnetic and nonferromagnetic structures are wedge-shaped.
10. A mixed-mu superconducting bearing, comprising:  
a rotor disposed for rotation adjacent a stationary superconductor material structure and a stationary permanent magnet structure, said rotor comprising steel pins embedded in a composite matrix.

11. The bearing as defined in claim 10, wherein said pins are staggered in an azimuthal direction.

12. The bearing as defined in claim 10, wherein at least a portion of said rotor is covered by a thin ferromagnetic sheet.

13. A mixed-mu superconducting bearing, comprising:  
a rotor disposed for rotation adjacent a stationary superconductor material structure and a stationary permanent magnet structure, said rotor having protruding portions on both a bottom surface and a top surface of said rotor.

14. The bearing as defined in claim 13, wherein both of said protruding portions are generally cone-shaped.

15. A mixed-mu superconducting bearing, comprising:  
a rotor disposed for rotation between a pair of stationary superconductor material structures, said pair of stationary superconductor structures being disposed between a pair of stationary permanent magnet structures.

16. The bearing as defined in claim 15, wherein said stationary permanent magnet structures are coupled by a rigid structure.


17. The bearing as defined in claim 15, wherein said rigid structure comprises iron.

18. The bearing as defined in claim 15, wherein said rotor comprises iron.


19. The bearing as defined in claim 15, wherein said bearing further includes stationary iron pieces disposed adjacent at least one of said stationary superconductor structures.

20. The bearing as defined in claim 15, wherein said bearing further includes supplemental stationary permanent magnets disposed adjacent at least one of said stationary superconductor structures and adjacent said rotor.


1/6




*Fig. 1*



*Fig. 2 (A)*




*Fig. 2 (B)*




2/6


Fig. 3



SUBSTITUTE SHEET (RULE 26)





*Fig. 4*



*Fig. 5*


SUBSTITUTE SHEET (RULE 26)






SUBSTITUTE SHEET (RULE 26)

5/6

*Fig. 8*



*Fig. 9*

# INTERNATIONAL SEARCH REPORT

International application No.  
PCT/US96/13927

## A. CLASSIFICATION OF SUBJECT MATTER

IPC(6) : G05G 1/00, 3/00

US CL : 74/572, 573R; 310/349; 505/166

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 74/572, 573R; 310/349; 505/166; 310/191, 90.5; 74/5.46, 5.7; 501/1

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

APS

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US, A, 5,177,387 (McMICHAEL ET AL.) 05 January 1993 (05/01/93), see col. 8, lines 5-59.	1-20
A	US, A, 5,330,967 (TAKAHATA ET AL.) 19 July 1994 (19/07/94), see Figures 1-8.	1-20
Y	US, A, 5,214,981 (WEINBERGER ET AL.) 01 June 1993 (01/06/93), see col. 2, line 31 through col. 5, line 27.	1-7, 15 and 18
A	US, A, 5,245,270 (AKIYAMA) 14 September 1993 (14/09/93), see Figures 1-5.	1-20
A	US, A, 5,314,868 (TAKAHATA ET AL.) 24 May 1994 (24/05/94), see Figs. 1, 3 and 4.	1-20

☒ Further documents are listed in the continuation of Box C. ☐ See patent family annex.

* Special categories of cited documents:	*T	later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
*A* document defining the general state of the art which is not considered to be of particular relevance	*X*	document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
*E* earlier document published on or after the international filing date	*Y*	document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
*L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	*Z*	document member of the same patent family
*O* document referring to an oral disclosure, use, exhibition or other means		
*P* document published prior to the international filing date but later than the priority date claimed		

Date of the actual completion of the international search

06 NOVEMBER 1996

Date of mailing of the international search report

31 JAN 1997

Name and mailing address of the ISA/US  
Commissioner of Patents and Trademarks  
Box PCT  
Washington, D.C. 20231

Facsimile No. (703) 305-3230

Authorized officer  
*Vinh T. Luong*  
VINH T. LUONG

Telephone No. (703) 308-3221

Form PCT/ISA/210 (second sheet)(July 1992)\*

# INTERNATIONAL SEARCH REPORT

International application No.  
PCT/US96/13927

## C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US, A, 4,498,048 (LEE ET AL.) 05 February 1985 (05/02/85), see Fig. 11.	1-20
A	US, A, 3,954,064 (MINOVITCH) 04 May 1976 (04/05/76), see Fig. 4.	1-20
A	US, A, 3,937,148 (SIMPSON) 10 February 1976 (10/02/76), see Fig. 5A.	1-20
A	US, A, 5,436,516 (YAMAZAKI ET AL.) 25 July 1995 (25/07/95), see Fig. 2.	1-20
A	US, A, 5,313,130 (SHIBAYAMA ET AL), 17 May 1994 (17/05/94), see Figures 1, 2 and 8.	1-20
A	US, A, 4,686,404 (NAKAZEKI ET AL.) 11 August 1987 (11/08/87), see Fig. 1.	1-20
A	US, A, 4,151,431 (JOHNSON) 24 August 1979 (24/08/79), see Fig. 10.	1-20
A	US, A, 5,220,232 (RIGNEY ET AL.) 15 June 1993 (15/06/93), see col. 4, lines 9-60.	1-20
A	US, A, 5,159,219 (CHU ET AL.) 27 October 1992 (27/10/92), see col. 8, lines 40-65.	1-20

Form PCT/ISA 210 (continuation of second sheet)(July 1992)\*

# INTERNATIONAL SEARCH REPORT

International application No.

PCT/US96/13927

## Box I Observations where certain claims were found unsearchable (Continuation of item 1 of first sheet)

This international report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☐ Claims Nos.:  
because they relate to subject matter not required to be searched by this Authority, namely:
2. ☐ Claims Nos.:  
because they relate to parts of the international application that do not comply with the prescribed requirements to such an extent that no meaningful international search can be carried out, specifically:
3. ☐ Claims Nos.:  
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

## Box II Observations where unity of invention is lacking (Continuation of item 2 of first sheet)

This International Searching Authority found multiple inventions in this international application, as follows:

Please See Extra Sheet.

1. ☒ As all required additional search fees were timely paid by the applicant, this international search report covers all searchable claims.
2. ☐ As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee.
3. ☐ As only some of the required additional search fees were timely paid by the applicant, this international search report covers only those claims for which fees were paid, specifically claims Nos.:
4. ☐ No required additional search fees were timely paid by the applicant. Consequently, this international search report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

Remark on Protest

☐

The additional search fees were accompanied by the applicant's protest.

☒

No protest accompanied the payment of additional search fees.

## INTERNATIONAL SEARCH REPORT

International application No.

PCT/US96/13927

### BOX II. OBSERVATIONS WHERE UNITY OF INVENTION WAS LACKING

This ISA found multiple inventions as follows:

- I. Claims 1-7, 15 and 18, drawn to the species of Figs. 1-2(B) that has special technical features such as a ferrite structure, a stationary superconductor material structure and a stationary permanent magnet structure.
- II. Claims 8-12, drawn to the species of Figs. 4-6 that has special technical features such as alternating ferromagnetic and nonferromagnetic structures and steel pins.
- III. Claims 13 and 14, drawn to the species of Fig. 7 that has special technical features such as generally cone-shaped protruding portions.
- IV. Claims 15-18, drawn to the species of Fig. 8 that has special technical features such as a pair of stationary superconductor material structures disposed between a pair of stationary permanent magnet structures.
- V. Claims 15, 19 and 20, drawn to the species of Fig. 9 that has special technical features such as stationary iron pieces disposed adjacent at least one of stationary superconductor structures and supplemental stationary permanent magnets.

**This Page is Inserted by IFW Indexing and Scanning  
Operations and is not part of the Official Record**

**BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☒ FADED TEXT OR DRAWING
- ☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☒ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☒ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: \_\_\_\_\_

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.**